

## Portland Cement (Ace #5359757) Uses



**QUIKRETE® Portland Cement (No. 1124-47)** complies with current ASTM C150 and Federal Specifications for portland cement. Can be mixed with aggregate and other ingredients to make concrete mix, mortar mix, and base coat stucco. Type I

**Available in:**  
47lb. bags

### To make Concrete Mix:

- 3 parts All-Purpose Gravel (No. 1151)
- 2 parts All-Purpose Sand (No. 1152)
- 1 part Portland Cement (by volume)

### To make Type S Mortar Mix:

- 3 1/2 to 4 1/2 parts Mason Sand (No. 1952)
- 1/2 part Hydrated Lime
- 1 part Portland Cement (by volume)

### Stucco

A finish composed of two or more layers of mortar (white or colored) that is applied to either indoor or outdoor walls.

Type S is sometimes specified for masonry at or below grade, but offers another quality. S has high compressive strength (1800 psi) but adds high tensile bond strength.